



BULLDOG® VOC Compliant Adhesion Promoter

GTPO125, QTPO125 (Gallon, Quart Liquid)



BULLDOG® VOC Compliant Adhesion Promoter has the same features and benefits of our current BULLDOG® Adhesion Promoter. It is a patent-pending, one-component formula that promotes adhesion on all types of automotive plastic.

- Compliant with South Coast AQMD Rule 1151 – Adhesion Promoter, effective 1/1/2010.
- Not for sale in Bay Area AQMD, Imperial Co APCD, and San Diego APCD
- Provides superior adhesion
- No waste – unused product can be poured back into the can
- One component formula
- Adds flexibility
- Fills 320 grit scratches

Compatible Coatings:

- All solvent-based urethane, epoxy, or acrylic lacquers, primers, sealers and basecoats.
- TPO125 is compatible with waterborne basecoat systems, as long as the primer is applied according to manufacturer's instructions.

Related Products:

EPC535 – BULLDOG® Abrasive Prep & Clean

Note: ETPO123B BULLDOG® Adhesion Promoter 15oz Aerosol is **not** affected by the above, and can be sold and used in the state of California. BULLDOG® Adhesion Promoter (QTPO123, GTPO123) will continue to be available in all areas of the country not subject to VOC restrictions.





BULLDOG® VOC Compliant Adhesion Promoter

DIRECTIONS FOR USE:

(Read all cautions and directions on the product label prior to use.)

Adhesion Promoter for Plastic Parts:

1. Clean all areas to be painted with BULLDOG® Abrasive Prep & Clean (see label for part# EPC535), using a gray scuff pad.
2. Rinse thoroughly with plenty of water. Wipe dry using a clean cloth and an air hose.
3. Sprinkle an area with water. If water sheets, you are ready to proceed with BULLDOG® application. If water beads, the cleaning steps 1-3 must be repeated.
4. Blow and tack surface.
5. Using a spray gun, apply an even, light coat. Wait 25 to 30 minutes before applying the next coating. *Dry times may vary based on temperature and humidity.*
6. Apply basecoat and clearcoat according to manufacturer's instructions.

Cleanup: All tools and spills should be cleaned immediately with Naked Gun® VOC Compliant Spray Gun Cleaner (CGC112) or Naked Gun® Spray Gun Paint Remover Aerosol (ENGC11131). Clean spray gun according to manufacturer's instructions.

Notes:

- BULLDOG® has a 24 hour open time. If the part is left longer than 24 hours, tack, and apply 1 even, light coat of BULLDOG® before applying basecoat or primer.
- Tint up to 30% with desired urethane or acrylic lacquer basecoat or toner for better hide. BULLDOG® may **not** be added to waterbased toners or basecoats.
- This product may not be compatible with all surfaces and all conditions surrounding application. Before applying to any surface, always test in an inconspicuous area to ensure no damage will result.
- Recommended HVLP Spray Gun Tip Size: 1.3mm – 1.4mm
- If thinning is necessary, BULLDOG® can be reduced up to 10% with KLEAN-STRIP® Acetone.





BULLDOG® VOC Compliant Adhesion Promoter

	GTP0125/QTPO125
Appearance	Liquid, mobile, hazy, light yellow to purple
Vapor Density	Heavier Than Air
Percent Volatile	Total Volatiles: 80.4% Water: 0% VOC Exempt: 57.7%
Flash Point	48°F
CPSC Flammability Classification	Flammable
Boiling Range	174°F to 375°F
VOC Category (Max Allowable VOC)	Adhesion Promoter (540 gm/liter)
Actual VOC	540 gm/liter 4.5 lbs/gal 22.7%
MAX Vapor Pressure of the V.O.C.:	11.4 mmHg @ 20°C
Storage	Store between 32°F and 95°F, in the original container.
Density	0.9 gm/liter 7.9 lb/gal
Shelf Life	2 years from date of manufacture, in an unopened container
DOT	UN1263, Paint Related Material, 3, PGII, Ltd. Qty
HAPS	Toluene, Xylene, Styrene, Ethyl Benzene
Coverage	250 – 425 sq. ft. per quart

ORDERING INFORMATION

Product	Size	Pack	Lbs	Case Cube	Unit Width	Unit Depth	Unit Height	UPC Code	Pallet Qty
QTPO125	QT	6	13	.406	3.44"	3.44"	8.72"	0 30192 12515 1	528
GTP0125	GL	4	35	.762	4.13"	6.63"	10.31"	0 30192 12525 0	208



©2012 W.M. Barr & Co., Inc.
P.O. Box 1879
Memphis, TN 38101
800.238.2672
www.bulldogsticks.com
www.kleanstripauto.com

